

ABSTRACT OF THE DISCLOSURE

An alkali development type photocurable composition comprises (A) an alkali-soluble macromolecular binder  
5 having a weight-average molecular weight in the range of 5,000 to 100,000 and an acid value in the range of 50 to 150 mg KOH/g, and obtained by causing (d) a compound possessing one glycidyl group in its molecule to react with a carboxyl group of (A-1) a copolymer of (a) an  
10 ethylenically unsaturated bond-containing compound possessing one carboxyl group in its molecule with (b) an ethylenically unsaturated bond-containing compound possessing neither hydroxyl group nor acidic group in its molecule, or a carboxyl group of (A-2) a copolymer of the  
15 compounds (a) and (b) mentioned above and (c) an ethylenically unsaturated bond-containing compound possessing a hydroxyl group and then causing (e) a polybasic acid anhydride to react with a hydroxyl group caused by the above reaction, (B) an inorganic powder, (C)  
20 a photopolymerizable monomer, (D) a photopolymerization initiator, and (E) an organic solvent. By using this composition, such calcined patterns as a conductor pattern and a dielectric pattern of high fineness may be formed by the photolithographic technique.

$A = d + (a+b) \neq A-1$  or  $a(A-2) = a+b+c$   
e.g. with A-1 or A-2 or A.